



Automotive Window Film	Visible Light Transmitted (VLT)	Total Solar Energy Rejected (TSER)	Infrared Rejection* (IRR)	Glare Reduction	UV Rejection
Crystalline 20	20%	62%	97%	77%	99%
Crystalline 40	39%	60%	97%	55%	99%
Crystalline 50	50%	56%	97%	44%	99%
Crystalline 60	60%	53%	97%	32%	99%
Crystalline 70	69%	50%	97%	22%	99%
Crystalline 80	77%	44%	96%	13%	99%
Crystalline 90	86%	34%	90%	3%	99%
Ceramic IR 5	6%	63%	95%	93%	99%
Ceramic IR 15	19%	59%	90%	78%	99%
Ceramic IR 25	30%	57%	90%	65%	99%
Ceramic IR 30	37%	55%	88%	57%	99%
Ceramic IR 35	45%	52%	85%	49%	99%
Ceramic IR 50	60%	47%	83%	32%	99%
Ceramic IR 70	78%	41%	78%	12%	99%
Color Stable 5	9%	57%	77%	90%	99%
Color Stable 20	19%	51%	68%	79%	99%
Color Stable 35	39%	40%	54%	56%	99%
Color Stable 50	52%	35%	49%	42%	99%
Obsidian 5	8%	44%	8%	91%	99%
Obsidian 15	19%	40%	9%	79%	99%
Obsidian 25	27%	38%	9%	69%	99%
Obsidian 30	39%	35%	9%	56%	99%
Obsidian 35	45%	33%	9%	49%	99%
Obsidian 40	54%	31%	7%	39%	99%
Obsidian 50	62%	28%	9%	30%	99%
Obsidian 80	78%	23%	7%	12%	99%
FX Premium 5	6%	45%	21%	93%	99%
FX Premium 15	17%	43%	18%	81%	96%
FX Premium 25	26%	41%	19%	71%	96%
FX Premium 30	35%	38%	22%	61%	96%
FX Premium 35	41%	37%	21%	54%	96%
FX Premium 55	58%	32%	23%	34%	96%

* Performance data generated using applicable industry test methods and standards. Infrared rejection measured on film only from 900nm to 1000nm.